

PRODUCT PROPERTIES													
Product Description	Shore A Hardness ±5	Operating Temperature °C Min.Max.	Application Temp °C Min.Max.	Tensile Strength Mpa (ISO 8339) / (ISO37)	Shear Strength Mpa (ASTM D1002)	Painable (Test is recommended)	Colours Available	Elongation at Break (%) (ASTM D1002)	Skin Time (Minutes) (23oC & 50%R.H)	Cure Rate (mm per 24hrs) (23oC & 50%R.H)	Dynamic Movement (%)	Package Size (mL)	Part number, Fix (Product Number) (Product Difference) (Colour)/Package in Litres: eg 300mL = L03or 600mL = L06)
<b>FIX8</b> Structural Adhesive Silicone	40	-40 +100	5 to 30	1.00	1.00	NO	BK,GY,TK, WH,TPAL	>300	30/12'	3	25	300 cart 600 foil	FIX8_ _ _
<b>FIX8 FN</b> Finishing Adhesive Silicone	35	-40 +100	5 to 30	1.00	1.00	NO	WH	>100	12	3	12.5	300 cart	FIX8FNWHL03
<b>FIX8 HT</b> High Tack Adhesive Silicone	50	-40 +100	5 to 30	1.00	1.00	NO	BK,WH, GY	>100	12	3	12.5	300 cart 600 foil	FIX8HT_ _ _
<b>FIX15</b> Multipurpose Adhesive Sealant	48	-40 +100	5 to 30	1.20/2.20	1.60	YES	BK,WH, GY	>300	15	3	25	290 cart 600 foil	MSP15_ _ _
<b>FIX190</b> High Strength Adhesive Sealant	45	-40 +100	5 to 30	1.60/3.60	1.60	YES	BK,WH	>230	45	3	20	290 cart 600 foil	MSP190_ _ _
<b>FIX190FWT</b> High Strength Adhesive Sealant	45	-40 +100	5 to 30	1.60/3.60	1.60	YES	BK,WH	>230	12	4	20	290 cart 600 foil	MSP190FWT_ _ _
<b>FIX200 Polymer &amp; Glass</b> Flexible Adhesive Silicone	25	-40 +100	5 to 30	0.75	0.75	NO	BK	600	30	1	50	310 cart	FS200BKL03
<b>FIXCLEAR 100%</b> Clear Adhesive Sealant	40	-40 +100	5 to 30	1.00	1.00	YES	Clear	>230	12	4	20	290 cart	MSPClearL03

FIX8AL and FIX8TP have 12mins working time.

**FixTech**  
Superior Bonding Solutions



**SUPERIOR  
BONDING  
PRODUCTS**

RECOMMENDED APPLICATIONS															
Product Description	Above & Below Waterline	Glazing Fixing & Finishing	Structural Fixing & Finishing	UV Stable Non-yellowing White	All Metals, Fibreglass	Aluminium & Stainless Steel	* Polymer Window	External Exposed Wipes	All Timber Types May Require Primer	Deck Gear & Fitting Seals	Deck to Hull Cabin Tops etc.	Teak Deck Caulking	Teak Deck Adhesion	Synthetic Deck Adhesion	100% Fuel & Solvent Resistant
<b>FIX8, FIX8FN, FIX8HT</b> Structural Silicone RTV-1 Bonding & Finishing (Anti-mould)		✓	✓	✓	✓	✓	✓	✓	✓	✓					
<b>FIX15</b> Multipurpose all purpose adhesive sealant	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓				
<b>FIX190, FIX190FWT</b> Multipurpose structural adhesive sealant	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓				
<b>FIX200 Polymer &amp; Glass *</b> Flexible Adhesive Silicone				✓	✓	✓	✓*	✓	✓						
<b>FIXCLEAR</b> Strongest 100% clear, adhesive sealant	✓	✓	✓		✓	✓		✓							
<b>FMP100 &amp; FMP200</b> Strongest one part 100% waterproof adhesive.	✓		✓		✓	✓		✓							
<b>FIX3</b> Synthetic Decking bedding adhesive			✓	✓	✓	✓		✓	✓	✓				✓	
<b>FIX30</b> Universal floor & tile bonding adhesive sealant			✓		✓	✓		✓					✓		
<b>FIX1DC Teak Deck Caulking</b> Cork, Teak, Synthetic decking				✓	✓	✓		✓	✓			✓			
<b>FM30 Fuel Sealant</b> US approved fuel resistant	✓		✓		✓	✓		✓							✓
<b>MP101</b> Extra Fine Poly White 2K Filler	✓**				✓	✓		✓							
<b>FIXSEAL FIX1060 1:1 Penetrating</b> Epoxy Solvent based sealer	✓				✓	✓		✓				✓			
<b>FIXSEAL FIX1070 1:1</b> Epoxy Flooring Waterbased sealer			Concrete & stone sealer						✓						
<b>FIX1210 1:1 Flexible Epoxy</b> bedding Adhesive	✓				✓	✓		✓					✓		✓
<b>FIX6060 2:1 Gel Epoxy</b> Lightweight Structural bonding	✓		✓		✓	✓		✓			✓				✓

\* Polymer window means window made from acrylic or polycarbonate  
 \*\* MP101 must be coated with marine paint for below waterline application  
 \*\*\* One component must be porous such as timber or structural foam core  
 \*\*\*\* Etch prime aluminium before bonding

Refer to [www.fixtech.com.au](http://www.fixtech.com.au) for application guideline sheet

**FixTech**  
Superior Bonding Solutions

**Technical Assistance :**

Fixtech LLC  
 1500 NW 52nd Street, Suite#508,  
 (W, Cypress Creek Road)  
 Ft.Lauderdale, Florida USA, 33309  
 Ph : +1 (954) 900 2916 Fx : +1 (954) 541 5918  
 Email: sales@fixtech.us

Fixtech Pty Ltd,  
 Unit 1, 20 Export Drv, Molendinar, QLD 4214.  
 P.O. Box 568, Southport, QLD 4215, AUSTRALIA  
 Ph : +61 (7) 55301099 Fx : +61 (7) 55301322 (Overseas)  
 Ph : 1300887077, Fx 1300887219 (Australia wide)  
 Email : info@fixtech.com.au

Fixtech International Limited, Taiwan Branch  
 96 Hongping Road, Siaogang, Kaohsiung City, 812, TAIWAN  
 Ph : +886 (7) 8062506 Fx : +886 (7) 8062811  
 Email : info@fixtech.asia

Fixtech International Limited, Zhuhai(Southern & Central China)  
 3rd F, Building 8, No.1 Pingdong Road, Nanping Technology Park,  
 Zhuhai City 519060, Guangdong, CHINA  
 Ph : +86 756 7750077 Fx : +86 756 8513101  
 Email : infochina@fixtech.com.cn



As a general guideline, to achieve successful adhesion, abrade and clean with Industrial Alcohol and ensure that the surface is dry and clean before adhering with Fixtech products. For further details, including TDS, MSDS and application hints and tips, please refer to our website: [www.fixtech.com.au](http://www.fixtech.com.au)



\*\* FM30 can be fully immersed in diesel after 7 days. Full property strength achieved after 7 days.

Product	Part	Volume	Weight	Color	Viscosity	Modulus	Strength	Temp	Adhesion	Application		
FIX6060L3	3Lt Kit	20	24hr	60	n/a	Transp	YES	>12	>60	-40 +100	n/a	Lightweight Structural bonding
FIX1210L20	20Lt Kit	18	24hr	120	60	Teak	YES	>14	>8	-40 -100	n/a	bedding Adhesive
FIX1060L	500mL 2L Kit	n/a	60 initial	30	n/a	Amber	YES	n/a	n/a	-40 +100	n/a	EPoxy Solvent based sealer
MP101	2kg Inc Activator	n/a	30	5	n/a	White	YES	n/a	n/a	-30 +115	78	FIXSEAL FIX1060 1:1 Penetrating Epoxy Solvent based sealer
MP101	MP101	n/a	30	5	n/a	White	YES	n/a	n/a	-30 +115	78	Extra Fine Poly White 2K Filler
FM30 Fuel Sealant	500mL 10:1 Kit	20	2kg inc	30	6	DK Grey	YES	>20	>20	-54 +121	60	US approved fuel resistant
FIX1DC	300 Cart 600 Foil	25	3	30	330	BK	NO	>10	>10	-40 +100	37	FIX1DC Teak Deck Caulking * Cork, Teak, Synthetic decking
FIX30	600 foil	20	1.5	40	300	WH	YES	>0.75	>0.75	-40 +100	n/a	Universal floor & tile bonding adhesive sealant
FIX3	600 foil	25	3	40	250	Teak	NO	1.00	1.00	-40 +100	40	Synthetic Decking bedding adhesive
FMP200	750 bottle	n/a	initial 24hr	30	n/a	Transp	YES	12.00	10.00	-40 +100	n/a	FIX3 Synthetic Decking bedding adhesive
FMP100	310 cart	n/a	initial 24hr	30	n/a	Transp	YES	12.00	10.00	-40 +100	n/a	FIX3 Synthetic Decking bedding adhesive